




STANDARD COLORS

Due to limitations in the printing process, please request actual color chips for accurate color viewing.




BUCKSKIN




PARCHMENT



ALMOND



AGED BRONZE



SHASTA WHITE




FOREST GREEN



PATINA GREEN



SIERRA TAN



MEDIUM BRONZE



CHARCOAL GREY



HEMLOCK GREEN



BRISTOL BLUE



TERRA-COTTA



DARK BRONZE



ZINC GREY




HARTFORD GREEN




ROYAL BLUE



COLONIAL RED




COPPER BROWN



MATTE BLACK



TEAL GREEN



BURGUNDY



DEEP RED

PREMIUM COLORS


Berridge premium colors require a nominal surcharge.



NATURAL WHITE




AWARD BLUE



CHAMPAGNE



COPPER-COTE™



ANTIQUE
COPPER-COTE

METALLIC COLORS


Berridge metallic colors are premium finishes which require a nominal surcharge.
Due to limitations in the printing process, please request actual color chips for accurate color viewing.

NATURAL METAL FINISH

Berridge Acrylic-Coated Galvalume® is a coated sheet product that combines the corrosion resistance of GALVALUME® steel sheet with a clear, organic resin applied to the top side and bottom side of GALVALUME® substrate.




ACRYLIC-COATED
GALVALUME®



ZINC-COTE™



LEAD-COTE™



PREWEATHERED
GALVALUME®



All colors except Award Blue comply with LEED® v3 & Energy Star requirements for roof slopes greater than 2:12.

Almond complies with LEED® v3 requirements for low slopes less than or equal to 2:12.

Natural White complies with LEED® v3 & Energy Star requirements for low slopes less than or equal to 2:12.

KYNAR 500® HYLAR 5000™ SPECIFICATIONS FOR GALVALUME® AND ALUMINUM* COIL COATING APPLICATIONS:

TESTED PROPERTY	TESTING METHOD	KYNAR 500® or HYLAR 5000™
Colors Available	---	See color chart on reverse side
Specular Gloss	ASTM D-523	Low and medium gloss only
Color Uniformity	ASTM D-2244	Color controlled both instrumentally and visually
Dry Film Thickness	ASTM D-7091, ASTM D-1005, NCCA 11-13, 11-14, 11-15	Primer 0.20 ± 0.05 mil, Topcoat 0.75 ± 0.05 mil
Hardness	ASTM D-3363, NCCA 11-12, Eagle Turquoise Pencils	HB Minimum
Adhesion (X-Cut)	ASTM D-3359	No adhesion loss
Adhesion (Crosshatch)	ASTM D-3359	No adhesion loss
Direct Impact Flexibility	ASTM D-2794, Gardner Impact Tester, 1/10" Distortion	Excellent, no removal
Reverse Impact Flexibility	NCCA Spec. 11, ASTM D-2794, Gardner Impact Tester, 5/8" ball Impact force in inch pounds equal to metal thickness	Excellent, no cracking or loss of adhesion
Formability	ASTM D-4145, 180° T-Bend on 1/8 Mandrel	No cracks or loss of adhesion
Salt Spray Resistance	ASTM B-117	Passes 2000 hrs on Galvalume® Passes 4000 hrs on Aluminum
Humidity Resistance	ASTM D-2247	Passes 2000 hrs on Galvalume® Passes 4000 hrs on Aluminum
Acid Resistance	ASTM D-1308, Proc. 3.1.1 10% Sulfuric Acid spot test, 24 hr exposure	Excellent, no effect
Alkali Resistance	ASTM D-1308, Proc. 5.2 10% Sodium Hydroxide, 24 hr exposure	Excellent, no effect
Abrasion Coefficient	ASTM D-968	100 liters/mil topcoat
Detergent Resistance	ASTM D-2248, 72 hrs immersion in 3% solution at 100°F	Excellent, no effect
Resistance to Acid Pollutants	ASTM D 1308 Proc. 3.1.1 24 hr exposure 10% HNO ³ vapors	Excellent, no effect
Weathering - Color Retention	ASTM D-2244, 20 yrs, 45° South Florida	Maximum 5 NBS units color change
Weathering - Chalk Resistance	ASTM D-4214, 20 yrs, 45° South Florida	Not worse than No. 8 rating
Erosion	20 yrs, 45° South Florida	Maximum 15% loss

Notes:

1. ASTM - American Society for Testing Materials
2. NCCA - National Coil Coaters Association
3. Galvalume® is 55% Aluminum-Zinc alloy coated sheet steel and is a registered trademark of BIEC International, Inc.

*Limited Availability for Aluminum, Consult Berridge

**BMC SAN ANTONIO
CORPORATE HQ**
6515 Fratt Rd
San Antonio, TX 78218
210-650-3050
Fax 210-650-0379

**BMC SEGUIN
MANUFACTURING**
2201 Rudeloff Rd
Seguin, TX 78155
830-401-5200
Fax 830-303-0530

**BMC HOUSTON
BRANCH FACILITY**
1720 Maury St
Houston, TX 77026
713-223-4971
Fax 713-236-9422

**BMC DALLAS
BRANCH FACILITY**
1940 W Northwest Hwy
Dallas, TX 75220
972-506-8496
Fax 972-506-8478

**BMC DENVER
BRANCH FACILITY**
7505 E 41st Ave
Denver, CO 80216
303-322-3703
Fax 303-322-3810

**BMC CHICAGO
BRANCH FACILITY**
1175 Carolina Dr
W Chicago, IL 60185
630-231-7495
Fax 630-231-7520

**BMC ATLANTA
BRANCH FACILITY**
319 Lee Ind'l Blvd
Austell, GA 30168
770-941-5141
Fax 770-941-7344

**BERRIDGE CALIFORNIA
SALES CORPORATION****
18732 Corby Ave
Artesia, CA 90701
562-402-2081
Fax: 562-865-7878



BERRIDGE MANUFACTURING COMPANY
www.berridge.com

Roofs of Distinction